

Transportation Management Tech Tips

United States Department of Agriculture
Forest Service



Technology &
Development Program

July 2004

7700

0477 1308—SDTDC

SEDIMENT MEASUREMENTS FROM MULTIPLE AGGREGATE SOURCES: NOT ALL AGGREGATES PERFORM IDENTICALLY

Randy B. Foltz, Research Engineer, Rocky Mountain Research Station, Moscow, ID

Mark Truebe, Geotechnical Engineer, Region 6, Willamette National Forest

BACKGROUND

The Rocky Mountain Research Station and the Willamette National Forest performed a study to investigate the sediment production of several aggregates. Nine basalts, three quartzites, two welded tuffs, two alluvial, and one each of glacial outwash and limestone were tested. Each aggregate was used widely, had a maximum size of 25 mm, and was dense graded. Of the aggregates studied, 11 were good and 7 were of marginal (but still useable) quality, as originally identified by the design engineers.

Test

Investigators ran a wide range of performance tests on all aggregates. Based on these tests results and test simplicity, the sand equivalent test was chosen as the single indicator of perceived aggregate quality.

Each aggregate received an initial simulated rainstorm, heavy truck traffic from a logging truck simulator, and a final simulated rainstorm with an intensity of 50 millimeters per hour and a duration of 30 minutes. By adding flow during the post-traffic storm, the impact of a longer cross-drain spacing was simulated. All work was done on a 6 percent road grade.

Results

The sediment production from the most erodible aggregate was 100 times that of the least erodible; a large range that should be considered when choosing aggregate surfacing material. Sediment production differences between the good and marginal aggregates became less apparent as either the distance between cross drains or the degree of rutting increased, suggesting the importance of timely maintenance to minimize deep rutting and establishment of the surface cross slope prior to heavy rainfall periods.

The best predictor of sediment production from each of the three road sections was the fraction passing the 0.6-mm sieve. Infiltration was controlled by the size of the pore space between the larger aggregates. Increasing fines filled the pore space and reduced infiltration, resulting in increased runoff. This greater runoff led to transport of the finer sizes and the observed higher sediment production.

These results suggest that to minimize sediment production one should minimize the fraction that is smaller than 0.6 mm. However, without sufficient fine material to hold the larger sizes in place, a loss of vehicle traction occurs. This tradeoff between sediment production and fines needed for aggregate stability is an ongoing topic of study.

The complete study was presented at the 2003 Low-Volume Roads Conference and is available on the web at <http://forest.moscowfs.wsu.edu/cgi-bin/engr/library/searchpub.pl?pub=2003c>.



**Approximate Metric to English
System Conversion Factors**

To Change	To	Multiply by
millimeters	inches	0.03937

**Approximate English to Metric
System Conversion Factors**

To Change	To	Multiply by
inches	millimeters	25.4

Information contained in this document has been developed for the guidance of employees of the Forest Service, United States Department of Agriculture (USDA), its contractors, and cooperating Federal and State agencies. The USDA Forest Service assumes no responsibility for the interpretation or use of this information by other than its own employees. The use of trade, firm, or corporation names is for the information and convenience of the reader. Such use does not constitute an official evaluation, conclusion, recommendation, endorsement, or approval of any product or service to the exclusion of others that may be suitable.



The U.S. Department of Agriculture (USDA) prohibits discrimination in all its programs and activities on the basis of race, color, national origin, sex, religion, age, disability, political beliefs, sexual orientation, or marital or family status. (Not all prohibited bases apply to all programs.) Persons with disabilities who require alternative means for communication of program information (Braille, large print, audiotape, etc.) should contact USDA's TARGET Center at (202) 720-2600 (voice and TDD).

To file a complaint of discrimination, write USDA, Director, Office of Civil Rights, Room 326-W, Whitten Building, 1400 Independence Avenue, SW, Washington, D.C. 20250-9410 or call (202) 720-5964 (voice and TDD). USDA is an equal opportunity provider and employer.